


TECHNICAL DATA SHEET [TDS]
PA66 Dinalon
REFERENCE: A1S25 G30-9159
PRODUCT DESCRIPTION

PA66 Dinalon, 30% Glass fibre, White

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1,38
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	9300
Stress at break (5 mm/min)	MPa	ISO 527	135
Tensile Stress at yield (5mm/min)	Mpa	ISO 527	139
Strain at break (5 mm/min)	%	ISO 527	2,9
Flexural modulus (2 mm/min)	MPa	ISO 178	
Flexural strength (2 mm/min)	MPa	ISO 178	210
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	5
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	35
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	240
VICAT softening temperature	°C	ISO 306	> 200
Burning rate	mm/min	ISO 3795	<100

UPDATE DATE

jun.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA66 Dinalon
REFERENCE: A1S25 G30-9159
PRODUCT DESCRIPTION

PA66 Dinalon, 30% Glass fibre, White

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	255-290
Recommended mould temperature	°C	-	70-100
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

jun.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

