


TECHNICAL DATA SHEET [TDS]
PA66 Dinalon
REFERENCE: A2X25 MI H-0055
PRODUCT DESCRIPTION

PA66 Dinalon, Medium impact, Heat stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.10
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	2500
Stress at break (50 mm/min)	MPa	ISO 527	50
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	63
Strain at break (50 mm/min)	%	ISO 527	> 20
Flexural modulus (2 mm/min)	MPa	ISO 178	2300
Flexural strength (2 mm/min)	MPa	ISO 178	90
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	18
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	65
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB

UPDATE DATE

mar.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA66 Dinalon
REFERENCE: A2X25 MI H-0055
PRODUCT DESCRIPTION

PA66 Dinalon, Medium impact, Heat stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	250-265
Recommended mould temperature	°C	-	60-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

mar.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

