


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1S25 G10DI-9102
PRODUCT DESCRIPTION

PA6 Dinalon, 10% Glass fibre, Dry impact, White

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.20
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	3800
Stress at break (5 mm/min)	MPa	ISO 527	64
Tensile Stress at yield (5mm/min)	Mpa	ISO 527	70
Tensile Strain at yield (5mm/min)	%	ISO 527	2,9
Strain at break (5 mm/min)	%	ISO 527	5,7
Flexural modulus (2 mm/min)	MPa	ISO 178	3500
Flexural strength (2 mm/min)	MPa	ISO 178	120
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	11
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	56
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	115
VICAT softening temperature	°C	ISO 306	> 200

UPDATE DATE

mar.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1S25 G10DI-9102
PRODUCT DESCRIPTION

PA6 Dinalon, 10% Glass fibre, Dry impact, White

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	240-270
Recommended mould temperature	°C	-	60-80
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

mar.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

