


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1S25 G30 H-0008
PRODUCT DESCRIPTION


PA6 Dinalon, 30% Glass fibre, Heat stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.36
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	9600
Stress at break (5 mm/min)	MPa	ISO 527	155
Strain at break (5 mm/min)	%	ISO 527	2.8
Flexural modulus (2 mm/min)	MPa	ISO 178	8600
Flexural strength (2 mm/min)	MPa	ISO 178	220
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	15
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	70
Tensile Stress at yield (5mm/min)	Mpa	ISO 527	166
Tensile Strain at yield (5mm/min)	%	ISO 527	2.7
Rheological			
Melt volume rate M.V.R. (275°C, 5 kg)	cm ³ /10min	ISO 1133	51,4
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	200
VICAT softening temperature	°C	ISO 306	> 200
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB

UPDATE DATE

dic.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1S25 G30 H-0008
PRODUCT DESCRIPTION

PA6 Dinalon, 30% Glass fibre, Heat stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	245-275
Recommended mould temperature	°C	-	60-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

dic.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

