


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1S25 M-0004
PRODUCT DESCRIPTION

PA6 Dinalon, Low friction, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.14
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	3000
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	75
Tensile Strain at yield (50mm/min)	%	ISO 527	3,6
Flexural modulus (2 mm/min)	MPa	ISO 178	2850
Flexural strength (2 mm/min)	MPa	ISO 178	100
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	2
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	>53
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB
Burning rate	mm/min	ISO 3795	<100
Processing			
Melt temperature range	°C	-	210-245
Recommended mould temperature	°C	-	70-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

