


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 G15 E-0007
PRODUCT DESCRIPTION

PA6 Dinalon, 15% Glass fibre, Food/ environmental grade, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.23
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	5650
Stress at break (5 mm/min)	MPa	ISO 527	120
Strain at yield (5 mm/min)	%	ISO 527	2,5
Flexural modulus (2 mm/min)	MPa	ISO 178	4700
Flexural strength (2 mm/min)	MPa	ISO 178	170
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	6
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	35
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	195
VICAT softening temperature	°C	ISO 306	> 200
Processing			
Melt temperature range	°C	-	245-275
Recommended mould temperature	°C	-	60-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

jun.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

