


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 HI-0002
PRODUCT DESCRIPTION

PA6 Dinalon, High impact, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1,07
Humidity	%	ISO 15512-B	<0,25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	1660
Stress at break (50 mm/min)	MPa	ISO 527	34
Strain at break (50 mm/min)	%	ISO 527	>20
Flexural modulus (2 mm/min)	MPa	ISO 178	1570
Flexural strength (2 mm/min)	MPa	ISO 178	61
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	60
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NR
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	44
Tensile Strain at yield (50mm/min)	%	ISO 527	4.2
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	48
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB

UPDATE DATE

sep.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 HI-0002
PRODUCT DESCRIPTION

PA6 Dinalon, High impact, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	240 - 260
Recommended mould temperature	°C	-	80 - 95
Drying temperature	°C	-	80
Drying time	h	-	4

UPDATE DATE

sep.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

