


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 HI-6005
PRODUCT DESCRIPTION

PA6 Dinalon, High impact, RAL 6005

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1,06
Humidity	%	ISO 15512-B	<0,25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	1650
Stress at break (50 mm/min)	MPa	ISO 527	35
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	42
Tensile Strain at yield (50mm/min)	%	ISO 527	3,9
Strain at break (50 mm/min)	%	ISO 527	60
Flexural modulus (2 mm/min)	MPa	ISO 178	1300
Flexural strength (2 mm/min)	MPa	ISO 178	50
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	63
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	50
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB

UPDATE DATE

jul.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 HI-6005
PRODUCT DESCRIPTION

PA6 Dinalon, High impact, RAL 6005

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	240-260
Recommended mould temperature	°C	-	65-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

jul.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

