


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 MI-0002
PRODUCT DESCRIPTION

PA6 Dinalon, Medium impact, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1,10
Humidity	%	ISO 15512-B	< 0.25
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	2200
Stress at break (50 mm/min)	MPa	ISO 527	40
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	59
Strain at yield (50 mm/min)	%	ISO 527	4,4
Strain at break (50 mm/min)	%	ISO 527	>30
Flexural modulus (2 mm/min)	MPa	ISO 178	2200
Flexural strength (2 mm/min)	MPa	ISO 178	82
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	18
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	50

UPDATE DATE

jul.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 MI-0002
PRODUCT DESCRIPTION

PA6 Dinalon, Medium impact, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	210-240
Recommended mould temperature	°C	-	50-80
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

jul.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

