


TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 V0-7035
PRODUCT DESCRIPTION

PA6 Dinalon, V0 Halogen free, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.18
Humidity	%	ISO 15512-B	< 0.25
Mould shrinkage, parallel	%	ISO 294-4	0.8 - 1.2
Mould shrinkage, normal	%	ISO 294-4	0.8 - 1.2
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	3400
Stress at break (50 mm/min)	MPa	ISO 527	70
Strain at yield (50 mm/min)	%	ISO 527	3.2
Strain at break (50 mm/min)	%	ISO 527	6.8
Flexural strength (2 mm/min)	MPa	ISO 178	97
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	2.5
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	60
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	V0
Glow wire flammability index, GWFI (2 mm)	°C	UNE-EN 60695-2-12	960

UPDATE DATE

abr.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PA6 Dinalon
REFERENCE: B1X25 V0-7035
PRODUCT DESCRIPTION

PA6 Dinalon, V0 Halogen free, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	210-240
Recommended mould temperature	°C	-	60-90
Drying temperature	°C	-	80
Drying time	h	-	2 - 4

UPDATE DATE

abr.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

