



TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S02 V2 UV-7035

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, V2 Halogen free, UV stabilized, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	0,93
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	1300
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	24
Tensile Strain at yield (50mm/min)	%	ISO 527	5,1
Strain at break (50 mm/min)	%	ISO 527	>80
Flexural modulus (2 mm/min)	MPa	ISO 178	1200
Flexural strength (2 mm/min)	MPa	ISO 178	32
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	23
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Rheological			
Melt flow index M.F.I. (230°C, 2.16 kg)	g/10 min	ISO 1133	3
Thermal			
Flammability classification (0,8mm)	V0-V1-V2-HB	UL 94	V2
Burning rate	mm/min	ISO 3795	<100

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.





TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S02 V2 UV-7035

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, V2 Halogen free, UV stabilized, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	175 - 210
Recommended mould temperature	°C	-	10 - 40

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

