


TECHNICAL DATA SHEET [TDS]
PP Dinaplen
REFERENCE: PPC1S08 UV-7286
PRODUCT DESCRIPTION

PP Copolymer Dinaplen, UV stabilized, Grey

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	0.92
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	1200
Stress at yield (50 mm/min)	MPa	ISO 527	23
Strain at yield (50 mm/min)	%	ISO 527	6.7
Strain at break (50 mm/min)	%	ISO 527	>200
Flexural strength (2 mm/min)	MPa	ISO 178	24
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	12
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Rheological			
Melt flow index M.F.I. (230°C, 2.16 kg)	g/10 min	ISO 1133	15
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	55
Processing			
Melt temperature range	°C	-	175-210
Recommended mould temperature	°C	-	10-40

UPDATE DATE

jul.-2010

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

