



TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S15 G30-4137

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, 30% Glass fibre, Black

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1,14
Ash content	%	ISO 3451	30
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	5800
Tensile Stress at yield (5mm/min)	Mpa	ISO 527	70
Tensile Strain at yield (5mm/min)	%	ISO 527	2.5
Strain at break (5 mm/min)	%	ISO 527	2.8
Flexural modulus (2 mm/min)	MPa	ISO 178	5800
Flexural strength (2 mm/min)	MPa	ISO 178	100
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	10
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	40
Rheological			
Melt flow index M.F.I. (230°C, 2.16 kg)	g/10 min	ISO 1133	14
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	135
Burning rate	mm/min	ISO 3795	<100

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.





TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S15 G30-4137

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, 30% Glass fibre, Black

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	190 - 240
Recommended mould temperature	°C	-	25 - 65

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

