



TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S15 G30-7329

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, 30% Glass fibre, Grey

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.12
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	6900
Stress at break (5 mm/min)	MPa	ISO 527	75
Strain at break (5 mm/min)	%	ISO 527	3.5
Flexural modulus (2 mm/min)	MPa	ISO 178	6900
Flexural strength (2 mm/min)	MPa	ISO 178	125
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	10
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	40
Rheological			
Melt flow index M.F.I. (230°C, 2.16 kg)	g/10 min	ISO 1133	14
Thermal			
Heat deflection temperature HDT (1.80MPa)	°C	ISO 75-A	148
Processing			
Melt temperature range	°C	-	210-250
Recommended mould temperature	°C	-	25-65

UPDATE DATE

may.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

