



## TECHNICAL DATA SHEET [TDS]

**PP Dinaplen**

**REFERENCE: PPC1S30 UV-7391**

### PRODUCT DESCRIPTION

PP Copolymer Dinaplen, UV stabilized, Grey

| PROPERTIES                                 | UNITS             | METHOD      | VALUE D.A.M |
|--------------------------------------------|-------------------|-------------|-------------|
| <b>Physical</b>                            |                   |             |             |
| Relative density                           | g/cm <sup>3</sup> | ISO 1183    | 0.92        |
| <b>Mechanical</b>                          |                   |             |             |
| Tensile modulus (1 mm/min)                 | MPa               | ISO 527     | 1350        |
| Stress at break (50 mm/min)                | MPa               | ISO 527     | 18          |
| Tensile Stress at yield (50mm/min)         | Mpa               | ISO 527     | 24          |
| Tensile Strain at yield (50mm/min)         | %                 | ISO 527     | 4           |
| Strain at break (50 mm/min)                | %                 | ISO 527     | >15         |
| Flexural modulus (2 mm/min)                | MPa               | ISO 178     | 1300        |
| Flexural strength (2 mm/min)               | MPa               | ISO 178     | 35          |
| Charpy notched impact strength (23°C)      | kJ/m <sup>2</sup> | ISO 179/1eA | 7           |
| Charpy unnotched impact strength (23°C)    | kJ/m <sup>2</sup> | ISO 179/1eU | NB          |
| <b>Rheological</b>                         |                   |             |             |
| Melt flow index M.F.I. (230°C, 2.16 kg)    | g/10 min          | ISO 1133    | 28          |
| <b>Thermal</b>                             |                   |             |             |
| Heat deflection temperature HDT (1.80 MPa) | °C                | ISO 75-A    | 53          |
| Burning rate                               | mm/min            | ISO 3795    | <100        |

### UPDATE DATE

ene.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.





## TECHNICAL DATA SHEET [TDS]

**PP Dinaplen**

**REFERENCE: PPC1S30 UV-7391**

### PRODUCT DESCRIPTION

PP Copolymer Dinaplen, UV stabilized, Grey

| PROPERTIES                    | UNITS | METHOD | VALUE D.A.M |
|-------------------------------|-------|--------|-------------|
| <b>Processing</b>             |       |        |             |
| Melt temperature range        | °C    | -      | 175-210     |
| Recommended mould temperature | °C    | -      | 10-40       |

### UPDATE DATE

ene.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

