



TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S30 UV-7414

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, UV stabilized, Grey

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	0.92
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	1300
Stress at break (50 mm/min)	MPa	ISO 527	19
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	24
Tensile Strain at yield (50mm/min)	%	ISO 527	4.1
Strain at break (50 mm/min)	%	ISO 527	>12
Flexural modulus (2 mm/min)	MPa	ISO 178	1250
Flexural strength (2 mm/min)	MPa	ISO 178	35
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	7
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	NB
Rheological			
Melt flow index M.F.I. (230°C, 2.16 kg)	g/10 min	ISO 1133	25
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	52

UPDATE DATE

ene.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.





TECHNICAL DATA SHEET [TDS]

PP Dinaplen

REFERENCE: PPC1S30 UV-7414

PRODUCT DESCRIPTION

PP Copolymer Dinaplen, UV stabilized, Grey

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	175-210
Recommended mould temperature	°C	-	10-40

UPDATE DATE

ene.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

