


TECHNICAL DATA SHEET [TDS]
PC Dinaxan
REFERENCE: PC1S15 G10V0-7035
PRODUCT DESCRIPTION

PC Dinaxan, 10% Glass fibre, V0 Halogen free, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.26
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	3700
Tensile Stress at yield (5mm/min)	Mpa	ISO 527	75
Tensile Strain at yield (5mm/min)	%	ISO 527	3,6
Flexural strength (2 mm/min)	MPa	ISO 178	120
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	5
Rheological			
Melt flow index M.F.I. (300°C, 1.2 kg)	g/10min	ISO 1133	12
Thermal			
VICAT softening temperature	°C	ISO 306-B50	144
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	V0
Burning rate	mm/min	ISO 3795	<100

UPDATE DATE

abr.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PC Dinaxan
REFERENCE: PC1S15 G10V0-7035
PRODUCT DESCRIPTION

PC Dinaxan, 10% Glass fibre, V0 Halogen free, RAL 7035

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	280 - 320
Recommended mould temperature	°C	-	80 - 120
Drying temperature	°C	-	120
Drying time	h	-	4

UPDATE DATE

abr.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

