



TECHNICAL DATA SHEET [TDS]

PC Dinaxan

REFERENCE: PC3S25 UV-0100

PRODUCT DESCRIPTION

PC Dinaxan, UV stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.20
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	2400
Stress at break (50 mm/min)	MPa	ISO 527	52
Tensile Stress at yield (50mm/min)	Mpa	ISO 527	62
Tensile Strain at yield (50mm/min)	%	ISO 527	5,3
Strain at break (50 mm/min)	%	ISO 527	> 70
Flexural modulus (2 mm/min)	MPa	ISO 178	2400
Flexural strength (2 mm/min)	MPa	ISO 178	96
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	12
Rheological			
Melt flow index M.F.I. (300°C, 1.2 kg)	g/10min	ISO 1133	20
Thermal			
VICAT softening temperature	°C	ISO 306	141
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	V2

UPDATE DATE

jun.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.




TECHNICAL DATA SHEET [TDS]
PC Dinaxan
REFERENCE: PC3S25 UV-0100
PRODUCT DESCRIPTION

PC Dinaxan, UV stabilized, Natural

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	270-300
Recommended mould temperature	°C	-	80-120
Drying temperature	°C	-	120
Drying time	h	-	4

UPDATE DATE

jun.-2018

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

