

Technical data sheet

Chemicals



EBA REPSOL EBANTIX[®] E1704

EBA REPSOL EBANTIX[®] E1704 is a copolymer suitable for blown film applications where good processability, flexibility and good mechanical properties are required. The butyl acrylate content is 17%. It contains antioxidant additives.

Applications

- Film extrusion.
- Stretch hood film.
- Cables.

Recommended melt temperature 180°C. Processing characteristics of E1704 are similar to LDPE and conventional polyethylene extruders are recommended. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
General			
Melt flow rate (190°C, 2.16kg)	0.4	g/10 min	ISO 1133
Butyl acrylate content	17	%	Internal
Density at 23°C	925	kg/m ³	ISO 1183
Melting Point	96	°C	Internal
Film⁽¹⁾			
Dart drop (F ₅₀)	1400	g	ISO 7765-1
Tear resistance (Elmendorf) (MD/TD)	360/390	cN	ISO 6383-2
Tensile strength at break (MD/TD)	29/30	MPa	ISO 527-3
Elongation at break (MD/TD)	750/850	%	ISO 527-3

(1) 100 µm thickness film, blow up ratio 1:2.5, frost line height 50 cm.

EBA REPSOL EBANTIX[®] E1704 complies with the European Directives regarding materials intended for contact with foodstuffs. The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

Storage

EBA REPSOL EBANTIX[®] E1704 should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 40°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and the properties of the transformed product.

January 2017

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Centre
Ctra. de Extremadura AS, Km 18
28931 Móstoles, Madrid
Tel. +34 91 753 06 00
atd_poliolefinas@repsol.com

Headquarters:
Méndez Álvaro, 44
28045 Madrid
Spain
www.chemicals.repsol.com

Customer Care:
sacrq@repsol.com