

Technical data sheet

Chemicals



EBA REPSOL EBANTIX® E27150

EBA REPSOL EBANTIX® E27150 offers excellent flexibility and is suitable for injection moulding. The butyl acrylate content is 20%. It contains antioxidant and free flowing agent.

Applications

- Hot Melt Adhesives.
- Packaging.
- Bookbinding.
- Carpet backing.

Recommended melt temperature 180°C. EBA copolymers exhibit excellent thermal stability, which allows higher processing temperatures if needed. Processing characteristics of E27150 are similar to LDPE and conventional polyethylene extruders are recommended. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
General			
Melt flow rate (190°C, 2.16kg)	150	g/10 min	ISO 1133
Butyl acrylate content	27	%	Internal
Density at 23°C	925	kg/m ³	ISO 1183
Melting Point	76	°C	Internal
Ring-ball softening point	100	°C	ASTM E-28
Mechanical			
Tensile stress at break	3	MPa	ISO 527-2
Elongation at break	550	%	ISO 527-2
Shore Hardness A	76	-	ISO 868

EBA REPSOL EBANTIX® E27150 complies with the European Directives regarding materials intended for contact with foodstuffs. The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

Storage

EBA REPSOL EBANTIX® E27150 should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 40°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and the properties of the transformed product.

January 2017

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Centre
Ctra. de Extremadura AS, Km 18
28931 Móstoles, Madrid
Tel. +34 91 753 86 00
atd_poliiolefinas@repsol.com

Headquarters:
Méndez Álvaro, 44
28045 Madrid
Spain
www.chemicals.repsol.com

Customer Care:
sacrq@repsol.com