



ISPLEN® PG370 AT

Polypropylene homopolymer, 30% chemically coupled fiber glass reinforced compound.

ISPLEN® PG370 AT shows a very high stiffness, keeping good impact strength at every range of temperatures. It also shows a low warpage and shrinkage behaviour. The product is high heat stabilised.

APPLICATIONS

- Automotive: Under the bonnet parts subjected to severe mechanical stresses (Light housings, heat and ventilation housings, filters)
- Technical pieces, in general.
- Electrical housings, power tools.
- Washing machines cylinders.

PROPERTIES	VALUE	UNIT	TEST METHOD
General			
MFI (230°C, 2.16Kg)	12,5	g/10min	ISO 1133
Density	1,14	g/cm ³	ISO 1183
Mechanical			
Flexural Modulus of Elasticity	5800	MPa	ISO 178
Tensile Strength at Break	88	MPa	ISO 527-2
Elongation at Break	4	%	ISO 527-2
Izod Impact Strength	23 °C notched / unnotched	10 / 55	KJ/m ²
	0 °C notched / unnotched	8 / 45	KJ/m ²
Thermal			
Vicat (10N, 120°/h)	163	°C	ISO 306
Viicat (50N, 120°/h)	133	°C	ISO 306
HDT (0,45 MPa)	158	°C	ISO 75
HDT (1,8 MPa)	140	°C	ISO 75
Others			
Shore D Hardness, 15s	78	°Shore	ISO 868
Shrinkage, 150x100x3mm	0,3– 0,6	%	ISO 2577

STORAGE

ISPLEN® PG370 AT should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes which may have a negative influence on the processability and the properties of the transformed product.

October 2009

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Centre
Ctra. de Extremadura A5, Km 18
28931 Móstoles, Madrid
Tel. +34 91 348 86 00
Fax: +34 91 530 45 17
atdpo@repsol.com

Headquarters:
Pº de la Castellana, 280
28046 Madrid
Spain
Tel. +34 91 348 29 56
www.chemicals.repsol.com

Customer Care:
sacrq@repsol.com