

Technical data sheet

Chemicals



EVA REPSOL PRIMEVA® P2735C

EVA resin REPSOL PRIMEVA® P2735C is especially suitable for HFFR and special cable compounds. It is also recommended for hot-melt adhesives and extrusion applications. EVA resin REPSOL PRIMEVA® P2735C presents low gel content. It contains antioxidant additive.

Applications

- Hot Melt Adhesives.
- Masterbatches.
- Microcellular foams.
- Sonic damping sheets.
- Film extrusion.
- Can be used to produce halogen-free-flame-retardant (HFFR) cables compounds.

Recommended melt temperature below 200°C to avoid the decomposition of the polymer. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
General			
Melt flow rate (190°C, 2.16kg)	3.5	g/10 min	ISO 1133
Vinyl acetate content	27	%	Internal
Density at 23 °C	953	kg/m ³	ISO 1183
Melting point	73	°C	Internal
Mechanical			
Tensile strength at break	23	MPa	ISO 527-2
Elongation at break	555	%	ISO 527-2
Shore A hardness	81	-	ISO 868

EVA REPSOL PRIMEVA® P2735C complies with the European Directives regarding materials intended for contact with foodstuffs. The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

Storage

EVA REPSOL PRIMEVA® P2735C should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 40°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and the properties of the transformed product.

January 2017

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Centre
Ctra. de Extremadura AS, Km 18
28931 Móstoles, Madrid
Tel. +34 91 753 06 00
atd_poliolefinas@repsol.com

Headquarters:
Méndez Álvaro, 44
28045 Madrid
Spain
www.chemicals.repsol.com

Customer Care:
sacrq@repsol.com