

fse tehnic_e_extrusion_verso_mai 4/15/2008 5:17:36 PM

extrusion solutions

LDPE Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
extrusion solutions LDPE B22/0.25	0,25	0,92	AOX	Blown film, shrink film
extrusion solutions LDPE B20/0.3	0,3	0,92		Blown film, heavy duty bags
extrusion solutions LDPE B21/0.5	0,5	0,92	S	Blown film, film for liquid packaging and co-extrusion
extrusion solutions LDPE B22/0.7	0,7	0,92	AOX	Blown film, agriculture film
extrusion solutions LDPE B22/1	1	0,92	AOX	Blown film, agriculture film
extrusion solutions LDPE B20/2	2	0,92		Blown film, thin film for fine packaging with good transparency
extrusion solutions LDPE B21/2	2	0,92	S	Blown film, thin film for fine packaging with good transparency
extrusion solutions LDPE B20/3	3	0,92		Blown film, thin film for extrafine packaging with good transparency
extrusion solutions LDPE B21/3	3	0,92	S	Blown film, thin film for extrafine packaging with good transparency

AOX – Antioxidants
S – slip agent

Rompotrol Petrochemicals S.R.L.
905700, Constanta, DJ 226, km 23, ROMANIA

T. (40) 241 50 68 68, F. (40) 241 50 69 09
E. office.petrochemicals@rompotrol.com

