

fise tehnic_blow_mai 4/16/2008 2:38:24 PM

blow
solutions

PP Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
blow solutions PPB200	0,55	0,91	B	Extrusion for pipes, sheets and blow moulding for bottles
blow solutions PPB300	0,85	0,91	B	Extrusion for pipes, sheets and blow moulding for bottles

HDPE Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
blow solutions HDPE5205B	0,25	0,95	B	Blow moulding, cans and containers up to 10L
blow solutions HDPE5305B	0,2	0,95	B	Blow moulding, bottles for chemicals and detergents max 50L, with good chemical resistance
blow solutions HDPE6205B	0,35	0,95	B	Blow moulding, cans and containers max 250L, with good chemical resistance

B – basic stabilization with antioxidants and halogen scavenger

Rompetro Petrochemicals S.R.L.
905700, Constanta, DJ 226, km 23, ROMANIA

T. (40) 241 50 68 68, F. (40) 241 50 69 09
E. office.petrochemicals@rompetrol.com
