

fse tehnic_e_extrusion_recto_m2.ai 4/18/2008 9:33:39 AM

extrusion solutions

PP Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
extrusion solutions PPF400BO1	2,2	0,91	B	Extrusion – biaxially oriented film
extrusion solutions PPF400BO1	3	0,91	B	Extrusion – biaxially oriented film
extrusion solutions PPF401	3	0,91	B	Extrusion – raffia tapes
extrusion solutions PPF401NHT	3	0,91	B NA	Extrusion – termoforming tapes
extrusion solutions PPF401NTT	3	0,91	B NA	Extrusion – termoforming tapes
extrusion solutions PPF500	8	0,91	B	Extrusion – cast film / film for general purpose packages
extrusion solutions PPS711	13	0,91	B	Extrusion – monofilaments and fibers
extrusion solutions PPS1001	24	0,91	B	Extrusion – monofilaments and fibers

HDPE Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
extrusion solutions HDPE RBF0.08	0,08	0,95	B	Blown film, general purpose film, packaging, bags with thickness more than 15 microns
extrusion solutions HDPE 5000S	0,85	0,95	B	Extrusion - fibers, ropes for general use

B – basic stabilization with antioxidants and halogen scavenger
NA – nucleating agent

Rompetro Petrochemicals S.R.L.
905700, Constanta, DJ 226, km 23, ROMANIA

T. (40) 241 50 68 68, F. (40) 241 50 69 09
E. office.petrochemicals@rompetrol.com

