

fise tehnic_injection_m.ai 4/18/2008 9:36:38 AM

injection solutions

PP Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
injection solutions PPJ500	5	0,91	B	Injection moulding, general purpose items
injection solutions PPJ700	12	0,91	B	Injection moulding, general purpose items
injection solutions PPJ800	16	0,91	B	Injection moulding, general purpose items
injection solutions PPJ900	20	0,91	B	Injection moulding, general purpose items
injection solutions PPJ1000	24	0,91	B	Injection moulding, general purpose items with thin walls
injection solutions PPJ1100	28	0,91	B	Injection moulding, general purpose items with thin walls
injection solutions PPJ1200	32	0,91	B	Injection moulding, general purpose items with thin walls
injection solutions PPJ1300	36	0,91	B	Injection moulding, general purpose items with thin walls
injection solutions PPJ1400	40	0,91	B	Injection moulding, general purpose items with thin walls

HDPE Grades

Grade	MFI (g / 10 min)	Density (g / cm ³)	Additives	Applications
injection solutions HDPE2200J	5	0,96	B	Injection moulding, crates, automotive parts
injection solutions HDPE2208J	5	0,96	B, UV	Injection moulding, crates, automotive parts
injection solutions HDPERBI 8.0	8	0,95	B	Injection moulding, housewares items, toys.

B – basic stabilization with antioxidants and halogen scavenger
UV – UV stabilizer

Rompetro Petrochemicals S.R.L.
905700, Constanta, DJ 226, km 23, ROMANIA

T. (40) 241 50 68 68, F. (40) 241 50 69 09
E. office.petrochemicals@rompetrol.com

