

LEXANT™ COPOLYMER HPH4404

REGION EUROPE

DESCRIPTION

High heat specialty polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO, steam, gamma and e-beam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	70	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	>112	%	ASTM D638
Tensile Modulus, 5 mm/min	2100	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2200	MPa	ASTM D790
Hardness, Rockwell M	85	-	ASTM D785
Hardness, Rockwell R	122	-	ASTM D785
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	85	%	ISO 527
Tensile Modulus, 1 mm/min	2150	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	66	MPa	ISO 178
Flexural Modulus, 2 mm/min	2120	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	NB3200	J/m	ASTM D4812
Izod Impact, notched, 23°C	600	J/m	ASTM D256
Izod Impact, notched, -30°C	120	J/m	ASTM D256
Tensile Impact Strength, Type S	577	kJ/m ²	ASTM D1822
Falling Dart Impact (D 3029), 23°C	149	J	ASTM D3029
Instrumented Dart Impact Total Energy, 23°C	120	J	ASTM D3763
Izod Impact, unnotched 80°10°3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10°3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°3 +23°C	53	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°3 -30°C	11	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°3 sp=62mm	57	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10°3 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10°3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	160	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	142	°C	ASTM D648

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	6.E-05	1 /°C	ASTM E83 1
CTE, -40°C to 40°C, xflow	8.E-05	1 /°C	ASTM E83 1
Specific Heat	1.25	J/g.°C	ASTM C351
Thermal Conductivity	0.21	W/m.°C	ASTM C177
CTE, -40°C to 40°C, flow	6.E-05	1 /°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1 /°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	154	°C	ISO 306
Vicat Softening Temp, Rate B/120	155	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Specific Gravity	1.2	-	ASTM D792
Specific Volume	0.83	cm³/g	ASTM D792
Density	1.19	g/cm³	ASTM D792
Water Absorption, (23°C/24hrs)	0.16	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	6	g/ 10 min	ASTM D1238
Melt Flow Rate, 330°C/2.16 kgf	30	g/ 10 min	ASTM D1238
Density	1.2	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.16	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.35	%	ISO 62
Melt Volume Rate, MVR at 330°C/2.16kg	29	cm³/ 10 min	ISO 1133
OPTICAL ⁽¹⁾			
Light Transmission, 2.54 mm	85	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
Refractive Index	1.6	-	ASTM D542
ELECTRICAL ⁽¹⁾			
Volume Resistivity	>2.6E+17	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	20.2	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.15	-	ASTM D150
Relative Permittivity, 1 MHz	3	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0012	-	ASTM D150
Dissipation Factor, 100 Hz	0.024	-	ASTM D150
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.