

LNPTM COLORCOMPTM COMPOUND E1000H

FORMERLY KNOWN AS "E-1000 EES"

DESCRIPTION

LNP COLORCOMP E1000H compound is based on unfilled Polyetherimide (PEI) resin. Added features of this grade include: Healthcare.

GENERAL INFORMATION

Features	Aesthetics/Visual effects, Healthcare/Formula lock, High temperature resistance, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY

Hygiene and Healthcare
Packaging

SUB INDUSTRY

Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	110	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	60	%	ASTM D638
Tensile Modulus, 5 mm/min	3580	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	165	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	3510	MPa	ASTM D790
Hardness, Rockwell M	109	-	ASTM D785
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	1335	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 6.4 mm, unannealed	207	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D648
CTE, -20°C to 150°C, flow	5.58E-05	1/°C	ASTM E831
Thermal Conductivity	0.22	W/m-°C	ASTM C177
Relative Temp Index, Elec ⁽²⁾	105	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	105	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	105	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.27	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.25	%	ASTM D570
Water Absorption, (23°C/Saturated)	1.25	%	ASTM D570

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.5 – 0.7	%	SABIC method
ELECTRICAL ⁽¹⁾			
Volume Resistivity	1.E+17	Ω.cm	ASTM D257
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101282876	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 400	°C	
Rear - Zone 1 Temperature	360 – 380	°C	
Middle - Zone 2 Temperature	370 – 390	°C	
Front - Zone 3 Temperature	380 – 400	°C	
Nozzle Temperature	390 – 400	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.