

LNPT[™] COLORCOMP[™] COMPOUND G1000EJ

DESCRIPTION

LNP COLORCOMP G1000EJ compound is based on unfilled Polysulfone (PSU) resin. Added features of this grade include: Low Extractables, Healthcare.

GENERAL INFORMATION

Features	Aesthetics/Visual effects, Food contact, Healthcare/Formula lock, High temperature resistance, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polysulfone (PSU)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Hygiene and Healthcare
Packaging

SUB INDUSTRY

Water Management
Home Appliances
Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial Packaging, Food & Beverage

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 50 mm/min	70.3	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	75	%	ASTM D638
Tensile Modulus, 50 mm/min	2480	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	106	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2690	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	69	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	174	°C	ASTM D648
CTE, -30°C to 30°C, flow	5.6E-5	1/°C	ASTM D696
PHYSICAL ⁽¹⁾			
Melt Flow Rate, 330°C/2.16 kgf	17	g/10 min	ASTM D1238
Specific Gravity	1.24	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.3	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.7	%	ASTM D955
ELECTRICAL ⁽¹⁾			
Volume Resistivity	5.0E+16	Ω.cm	ASTM D257
Dissipation Factor, 50/60 Hz	3.03	-	ASTM D150
Dissipation Factor, 1 kHz	3.04	-	ASTM D150
Dissipation Factor, 1 MHz	3.02	-	ASTM D150
INJECTION MOLDING ⁽³⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	135 – 163	°C	
Drying Time	3.5	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	329 – 385	°C	
Mold Temperature	140	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.