

LNPTM COLORCOMPTM COMPOUND J1000Z-WH9G618

J1000Z-WH9G618

DESCRIPTION

LNP COLORCOMP J1000-WH9G618 compound is based on Polyethersulfone (PES) resin. Added features of this grade include: Extrusion, Customer Specific Color.

GENERAL INFORMATION

Features	Aesthetics/Visual effects, High temperature resistance
Fillers	Unreinforced
Polymer Types	Polyethersulfone (PESU)
Processing Techniques	Injection Molding, Extrusion

INDUSTRY

Automotive
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Interiors
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	85	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Flexural Stress, yield, 2 mm/min	131	MPa	ISO 178
Flexural Modulus, 2 mm/min	2800	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	5.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	6.2E-05	1/°C	ISO 11359-2
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	0.6 – 0.8	%	SABIC method
Density	1.38	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.6	%	ISO 62-1
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.05	%	
Melt Temperature	355 – 370	°C	
Front - Zone 3 Temperature	370 – 380	°C	
Middle - Zone 2 Temperature	360 – 370	°C	
Rear - Zone 1 Temperature	345 – 355	°C	
Mold Temperature	140 – 150	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.