

LNPT[™] COLORCOMP[™] COMPOUND WQ117945

DESCRIPTION

LNP COLORCOMP COMPOUND WQ117945 is a PET based masterbatch for foaming applications containing a nanostructured, non-mineral based additive. Typical usage levels in final foam formulations are below 5%.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL			
Glass Transition Temperature (T _g)	79	°C	ISO 11357-2
Melting Temperature (T _m)	250	°C	ISO 11357-3
Crystallinity ⁽¹⁾	32	%	-
Ash Content ⁽²⁾	<0.05	%	ISO 3451
PHYSICAL			
Melt Volume Rate, MVR at 260°C/1.2 kg	25	cm ³ /10 min	ISO 1133
Bulk Density ⁽³⁾	0.7	g/cm ³	ASTM D1895
Density ⁽⁴⁾	1.06	g/cm ³	ASTM D1505

(1) Crystallinity in pellets

(2) 1 hour at 600 °C

(3) Pour Density

(4) Pellet Density

PROCESSING CONDITIONS

Processing	Values
Maximum melt temperature	300 °C
Drying Temperature	150-160 °C
Drying time	6-12 hours
Dew Point of Drying Air	< -20 °C
AirFlow Rate	2.2 m ³ /h/kg

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.