

# LNPT<sup>™</sup> ELCREST<sup>™</sup> CRX941 1W

## DESCRIPTION

LNP ELCRES CRX941 1W is an amorphous Polycarbonate (PC) copolymer resin that offers medium flow, UL V0 rating @ 1.6 mm for all colors, and high ductility in combination with excellent chemical resistance. This grade is available for custom coloring and may be an excellent candidate for a wide variety of applications that need improved chemical resistance. This grade is subjected to SABIC healthcare management of change policy and formulation lock.

### GENERAL INFORMATION

|                       |                                                                                                         |
|-----------------------|---------------------------------------------------------------------------------------------------------|
| Features              | Flame Retardant, Chemical Resistance, Healthcare/Formula lock, Impact resistant, Low temperature impact |
| Fillers               | Unreinforced                                                                                            |
| Brands                | LNPT <sup>™</sup> ELCREST <sup>™</sup>                                                                  |
| Polymer Types         | Polycarbonate (PC)                                                                                      |
| Processing Techniques | Injection Molding                                                                                       |

### INDUSTRY

Consumer  
Hygiene and Healthcare

### SUB INDUSTRY

Consumer Goods, Personal Accessory, Home Appliances, Commercial Appliance  
Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES                                               | TYPICAL VALUES | UNITS | TEST METHODS |
|----------------------------------------------------------|----------------|-------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>                         |                |       |              |
| Tensile Stress, yld, Type I, 50 mm/min                   | 52             | MPa   | ASTM D638    |
| Tensile Stress, brk, Type I, 50 mm/min                   | 59             | MPa   | ASTM D638    |
| Tensile Strain, yld, Type I, 50 mm/min                   | 6              | %     | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min                   | >100           | %     | ASTM D638    |
| Tensile Modulus, 50 mm/min                               | 1920           | MPa   | ASTM D638    |
| Flexural Modulus, 1.3 mm/min, 50 mm span                 | 2000           | MPa   | ASTM D790    |
| Flexural Strength, 1.3 mm/min, 50 mm span <sup>(2)</sup> | 85             | MPa   | ASTM D790    |
| Tensile Stress, yield, 50 mm/min                         | 50             | MPa   | ISO 527      |
| Tensile Stress, break, 50 mm/min                         | 57             | MPa   | ISO 527      |
| Tensile Strain, yield, 50 mm/min                         | 6              | %     | ISO 527      |
| Tensile Strain, break, 50 mm/min                         | >100           | %     | ISO 527      |
| Tensile Modulus, 1 mm/min                                | 1858           | MPa   | ISO 527      |
| Flexural Strength, 2 mm/min <sup>(2)</sup>               | 80             | MPa   | ISO 178      |
| Flexural Modulus, 2 mm/min                               | 2012           | MPa   | ISO 178      |
| <b>IMPACT <sup>(1)</sup></b>                             |                |       |              |
| Izod Impact, notched, 23°C                               | 765            | J/m   | ASTM D256    |
| Izod Impact, notched, -30°C                              | 680            | J/m   | ASTM D256    |
| Izod Impact, notched, -60°C                              | 609            | J/m   | ASTM D256    |
| Izod Impact, notched, -70°C                              | 570            | J/m   | ASTM D256    |
| Izod Impact, unnotched, 23°C                             | NB             | J/m   | ASTM D4812   |

© 2023 Copyright by SABIC. All rights reserved

**CHEMISTRY THAT MATTERS<sup>™</sup>**

| PROPERTIES                                                 | TYPICAL VALUES | UNITS                   | TEST METHODS   |
|------------------------------------------------------------|----------------|-------------------------|----------------|
| Izod Impact, unnotched, -70°C                              | NB             | J/m                     | ASTM D4812     |
| Instrumented Dart Impact Ductility, 23°C <sup>(3)</sup>    | 100            | %                       | ASTM D3763     |
| Instrumented Dart Impact Total Energy, 23°C <sup>(3)</sup> | 61             | J                       | ASTM D3763     |
| Izod Impact, notched 80*10*3 +23°C                         | 55             | kJ/m <sup>2</sup>       | ISO 180/1A     |
| Izod Impact, notched 80*10*3 -70°C                         | 35             | kJ/m <sup>2</sup>       | ISO 180/1A     |
| Izod Impact, unnotched 80*10*3 +23°C                       | NB             | kJ/m <sup>2</sup>       | ISO 180/1U     |
| Izod Impact, unnotched 80*10*3 -70°C                       | NB             | kJ/m <sup>2</sup>       | ISO 180/1U     |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm                 | 65             | kJ/m <sup>2</sup>       | ISO 179/1eA    |
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm                 | NB             | kJ/m <sup>2</sup>       | ISO 179/1eU    |
| Charpy -70°C, Unnotch Edgew 80*10*3 sp=62mm                | NB             | kJ/m <sup>2</sup>       | ISO 179/1eU    |
| <b>THERMAL <sup>(1)</sup></b>                              |                |                         |                |
| HDT, 1.82 MPa, 3.2mm, unannealed                           | 125            | °C                      | ASTM D648      |
| HDT, 0.45 MPa, 3.2 mm, unannealed                          | 138            | °C                      | ASTM D648      |
| Vicat Softening Temp, Rate B/50                            | 142            | °C                      | ASTM D1525     |
| Vicat Softening Temp, Rate B/120                           | 146            | °C                      | ASTM D1525     |
| CTE, -40°C to 40°C, flow                                   | 7E-05          | 1/°C                    | ASTM E831      |
| CTE, -40°C to 40°C, xflow                                  | 7E-05          | 1/°C                    | ASTM E831      |
| Ball Pressure Test, 125°C +/- 2°C                          | PASS           | -                       | IEC 60695-10-2 |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm                      | 123            | °C                      | ISO 75/Af      |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm                     | 137            | °C                      | ISO 75/Bf      |
| Vicat Softening Temp, Rate B/50                            | 142            | °C                      | ISO 306        |
| Vicat Softening Temp, Rate B/120                           | 144            | °C                      | ISO 306        |
| CTE, -40°C to 40°C, flow                                   | 7E-05          | 1/°C                    | ISO 11359-2    |
| CTE, -40°C to 40°C, xflow                                  | 7E-05          | 1/°C                    | ISO 11359-2    |
| <b>PHYSICAL <sup>(1)</sup></b>                             |                |                         |                |
| Specific Gravity                                           | 1.2            | -                       | ASTM D792      |
| Melt Volume Rate, MVR at 300°C/1.2 kg                      | 9.5            | cm <sup>3</sup> /10 min | ASTM D1238     |
| Melt Flow Rate, 300°C/1.2 kgf                              | 10             | g/10 min                | ASTM D1238     |
| Density                                                    | 1.19           | g/cm <sup>3</sup>       | ISO 1183       |
| Moisture Absorption, (23°C/50% RH/24hrs)                   | 0.08           | %                       | ISO 62-4       |
| Water Absorption, (23°C/24hrs)                             | 0.3            | %                       | ISO 62-1       |
| Melt Volume Rate, MVR at 300°C/1.2 kg                      | 9              | cm <sup>3</sup> /10 min | ISO 1133       |
| Mold Shrinkage, flow <sup>(4)</sup>                        | 0.4 – 0.9      | %                       | SABIC method   |
| Mold Shrinkage, xflow <sup>(4)</sup>                       | 0.4 – 0.9      | %                       | SABIC method   |
| <b>ELECTRICAL <sup>(1)</sup></b>                           |                |                         |                |
| Comparative Tracking Index (UL) {PLC} <sup>(5)</sup>       | 3              | PLC Code                | UL 746A        |
| Hot-Wire Ignition (HWI), PLC 0 <sup>(5)</sup>              | ≥0.8           | mm                      | UL 746A        |
| High Amp Arc Ignition (HAI), PLC 0 <sup>(5)</sup>          | ≥0.8           | mm                      | UL 746A        |
| <b>Dielectric Constant</b>                                 |                |                         |                |
| 100 MHz                                                    | 2.82           | -                       | SABIC method   |
| 2.47 GHz                                                   | 2.78           | -                       | SABIC method   |
| <b>Dissipation Factor</b>                                  |                |                         |                |
| 100 MHz                                                    | 0.0066         | -                       | SABIC method   |
| 2.47 GHz                                                   | 0.0053         | -                       | SABIC method   |
| Surface Resistivity                                        | >1.E+13        | Ω                       | ASTM D257      |

| PROPERTIES                                             | TYPICAL VALUES                    | UNITS | TEST METHODS |
|--------------------------------------------------------|-----------------------------------|-------|--------------|
| Volume Resistivity                                     | >1.E+15                           | Ω.cm  | ASTM D257    |
| <b>FLAME CHARACTERISTICS <sup>(5)</sup></b>            |                                   |       |              |
| UL Yellow Card Link                                    | <a href="#">E121562-104302666</a> | -     | -            |
| UL Recognized, 94V-0 Flame Class Rating <sup>(5)</sup> | ≥1.6                              | mm    | UL 94        |
| <b>INJECTION MOLDING <sup>(6)</sup></b>                |                                   |       |              |
| Drying Temperature                                     | 120                               | °C    |              |
| Drying Time                                            | 3 – 4                             | Hrs   |              |
| Drying Time (Cumulative)                               | 12                                | Hrs   |              |
| Maximum Moisture Content                               | 0.02                              | %     |              |
| Melt Temperature                                       | 290 – 340                         | °C    |              |
| Rear - Zone 1 Temperature                              | 270 – 320                         | °C    |              |
| Middle - Zone 2 Temperature                            | 280 – 330                         | °C    |              |
| Front - Zone 3 Temperature                             | 290 – 340                         | °C    |              |
| Nozzle Temperature                                     | 290 – 340                         | °C    |              |
| Mold Temperature                                       | 80 – 110                          | °C    |              |
| Back Pressure                                          | 0.3 – 0.7                         | MPa   |              |
| Screw Speed                                            | 50 – 100                          | rpm   |              |
| Shot to Cylinder Size                                  | 40 – 80                           | %     |              |
| Vent Depth                                             | 0.025 – 0.076                     | mm    |              |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Stress at yield

(3) at 3.3 m/s dart speed

(4) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(5) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(6) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.