

LNPTTM ELCRESTTM DMX1233

DESCRIPTION

LNP ELCRES DMX1233 is a UV stabilized improved flow Polycarbonate (PC) copolymer resin. Available in both transparent and custom colours, this grade is a good candidate for 5G related devices, anti-scratch covers etc. Added features of this grade include: Improved Scratch Resistance and Improved Dielectric Performance (lower Df).

GENERAL INFORMATION

Features	Good Processability, Dielectrics, Amorphous, IR Transparent, Scratch Resistance, Transparent/Translucent, Weatherable/UV stable, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Interiors
Personal Accessory
Electronic Components
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 50 mm/min	58.4	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	42.3	%	ASTM D638
Tensile Modulus, 50 mm/min	2505	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	108	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Tensile Stress, break, 50 mm/min	56.5	MPa	ISO 527
Tensile Strain, break, 50 mm/min	29.9	%	ISO 527
Tensile Modulus, 1 mm/min	2384	MPa	ISO 527
Flexural Strength, 2 mm/min	104	MPa	ISO 178
Flexural Modulus, 2 mm/min	2303	MPa	ISO 178
Pencil Hardness test, 1kgf	HB	-	ASTM D3363
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	45	J/m	ASTM D256
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, notched 80°10°4 +23°C	4.37	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	NB	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	3	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	134	°C	ASTM D648

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	133	°C	ISO 75 /Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	117	°C	ISO 75 /Af
CTE			
-40°C to 80°C, flow	7.5E-5	1/°C	ISO 11359-2
-40°C to 80°C, xflow	8.1E-5	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	146	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	139	°C	ISO 306
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.1827	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.037	%	ASTM D570
Melt Flow Rate, 300°C/ 1.2 kgf	21	g/10 min	ASTM D1238
Mold Shrinkage, flow ⁽³⁾	0.73	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.72	%	SABIC method
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.1 GHz	2.76	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0037	-	SABIC method
Dielectric Constant, 1.9 GHz	2.77	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0035	-	SABIC method
Dielectric Constant, 5 GHz	2.77	-	SABIC method
Dissipation Factor, 5 GHz	0.0032	-	SABIC method
Dielectric Constant, 10 GHz	2.87	-	SABIC method
Dissipation Factor, 10 GHz	0.0033	-	SABIC method
Dielectric Constant, 20 GHz	2.73	-	SABIC method
Dissipation Factor, 20 GHz	0.0035	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-104568852	-	-
UL Recognized, 94HB Flame Class Rating	≥0.6	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	70 – 95	°C	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.