

LNPT[™] ELCREST[™] ML4412

DESCRIPTION

LNP ELCRES ML4412 is based on Polycarbonate (PC) siloxane copolymer resin containing 20% glass fiber, medium flow, impact modified injection moldable grade. This grade is available in opaque colors only and is an excellent candidate for a broad range of applications that require a combination of stiffness and ductility.

GENERAL INFORMATION

Features	High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY

Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical, Material Handling, Defense

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	100	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	6300	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5800	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	110	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	6500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	165	MPa	ISO 178
Flexural Modulus, 2 mm/min	5700	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	700	J/m	ASTM D4812
Izod Impact, notched, 23°C	140	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	25	J	ASTM D3763
Izod Impact, notched 80°10'3 +23°C	17	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'3 -30°C	12	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'3 sp=62mm	17	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10'3 sp=62mm	12	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	132	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	2.6E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	137	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	133	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.33	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.2 – 0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽³⁾	0.4 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	11	g/10 min	ASTM D1238
Density	1.33	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.1	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Dielectric Constant (Dk), 1.1 GHz	3.11	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.0064	-	ASTM ES 7-83
Dielectric Constant, 1.9 GHz	3.13	-	SABIC method
Dissipation Factor, 1.9 GHz	0.006	-	SABIC method
Dielectric Constant, 5 GHz	3.14	-	SABIC method
Dissipation Factor, 5 GHz	0.0051	-	SABIC method
Dielectric Constant, 10 GHz	3.16	-	SABIC method
Dissipation Factor, 10 GHz	0.0063	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-104298581	-	-
UL Recognized, 94HB Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110	°C	
Drying Time	3 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.