

LNPT[™] FARADEx[™] COMPOUND 9X23246

DESCRIPTION

LNPT FARADEx 9X23246 compound is based on Polycarbonate/Acrylonitrile Styrene Acrylate (PC/ASA) blend containing a stainless steel fiber. Added features of this grade include: Electrically Conductive, EMI/RFI shielding

GENERAL INFORMATION

Features	Electrically Conductive, EMI/RFI Shielding, No PFAS intentionally added
Fillers	Stainless Steel Fiber
Polymer Types	Polycarbonate + ASA (PC+ASA)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Electrical and Electronics

SUB INDUSTRY

Automotive Interiors
Electrical Components and Infrastructure

TYPICAL PROPERTY VALUES

Revision 20240201

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Tensile Strain, break, 5 mm/min	45	%	ISO 527
Tensile Nominal Strain, break, 5 mm/min	5	%	ISO 527
Tensile Stress, yield, 5 mm/min	53	MPa	ISO 527
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
Flexural Strength, 2 mm/min	85	MPa	ISO 178
Tensile Modulus, 5 mm/min	2700	MPa	ASTM D638
Tensile Stress, yld, Type I, 5 mm/min	53	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	6	%	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	2700	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	65	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	60	kJ/m ²	ISO 179/1eU
Izod Impact, notched, 23°C	130	J/m	ASTM D256
Izod Impact, notched, -30°C	85	J/m	ASTM D256
Izod Impact, unnotched, 23°C	850	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	850	J/m	ASTM D4812
THERMAL ⁽¹⁾			

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	112	°C	ISO 75 /Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	127	°C	ISO 75 /Bf
Vicat Softening Temp, Rate B/50	132	°C	ISO 306
Vicat Softening Temp, Rate B/120	134	°C	ISO 306
CTE, 23°C to 50°C, flow	5.0E-05	1/°C	ISO 11359-2
CTE, 23°C to 50°C, xflow	6.0E-05	1/°C	ISO 11359-2
HDT, 1.82 MPa, 3.2mm, unannealed	112	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	127	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.23	g/cm³	ISO 1183
Specific Gravity	1.23	-	ASTM D792
Mold Shrinkage, flow	0.1 – 0.3	%	SABIC method
Mold Shrinkage, xflow	0.1 – 0.4	%	SABIC method
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Water Absorption, (23°C/ saturated)	0.4	%	ASTM D570
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.0E+01 – 1.0E+03	Ω	ASTM D257
Volume Resistivity	1.0E+02 – 1.0E+04	Ω.cm	ASTM D4496
Shielding Effectiveness @ 3mm	50 – 65	dB	SABIC method
Static Decay, 5000V to <50V	<0.01	Seconds	FTMS101B
INJECTION MOLDING ⁽²⁾			
Drying Temperature	100 – 110	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 290	°C	
Rear - Zone 1 Temperature	240 – 270	°C	
Middle - Zone 2 Temperature	250 – 280	°C	
Front - Zone 3 Temperature	260 – 290	°C	
Nozzle Temperature	260 – 290	°C	
Mold Temperature	60 – 90	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™