

LNPT™ KONDUIT™ COMPOUND OX10324

DESCRIPTION

LNP KONDUIT OX10324 compound is based on Polyphenylene Sulfide (PPS) resin containing glass fiber and proprietary thermal filler. Added features of this grade include: Thermally Conductive and Non-Brominated, Non-Chlorinated Flame Retardant.

GENERAL INFORMATION

Features	Flame Retardant, Thermally Conductive, Non Cl/Br flame retardant, No PFAS intentionally added
Fillers	Glass Fiber, Proprietary Filler
Polymer Types	Polyphenylene Sulfide, Linear (PPS, Linear)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Home Appliances
Mobile Phone - Computer - Tablets, Lighting
Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	49	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	0.6	%	ASTM D638
Tensile Modulus, 5 mm/min	13500	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	75	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	15600	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	53	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.6	%	ISO 527
Tensile Modulus, 1 mm/min	14000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	13500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	70	J/m	ASTM D4812
Izod Impact, notched, 23°C	24	J/m	ASTM D256
Izod Impact, unnotched 80°10°4 +23°C	7	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm	275	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	258	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.32E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	2.5E-05	1/°C	ASTM E831
Thermal Conductivity through-plane, 60°60°3mm plaque	1.3	W/m-K	ISO 22007-2

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Thermal Conductivity in-plane, 60*60*3mm plaque	18	W/m-K	ISO 22007-2
Thermal Conductivity through-plane, 10*10*3mm sample	3.5	W/m-K	ASTM E1461-07
Thermal Conductivity in-plane, 25*0.4mm disc	15	W/m-K	ASTM E1461-07
CTE, -30°C to 80°C, flow	1.3E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	2.39E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	1.38E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	2.44E-05	1/°C	ISO 11359-2
Ball Pressure Test, 165°C +/- 2°C	PASSES	-	IEC 60695-10-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	231	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	130	°C	UL 746B
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.1 – 0.2	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.1 – 0.3	%	ISO 294
Density	1.75	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.01	%	ISO 62-1
Water Absorption, 23°C/24hrs	0.01	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity	>2.5E+04	Ω	ASTM D257
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥1.2	mm	UL 746A
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101344589	-	-
UL Yellow Card Link 2	E207780-100960980	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.2	mm	UL 94
Glow Wire Ignitability Temperature, 1.0 mm ⁽⁴⁾	850	°C	IEC 60695-2-13
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	320 – 350	°C	
Front - Zone 3 Temperature	315 – 345	°C	
Middle - Zone 2 Temperature	315 – 345	°C	
Rear - Zone 1 Temperature	315 – 345	°C	
Mold Temperature	110 – 150	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	
Shot to Cylinder Size	50 – 75	%	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Value shown here is based on internal measurement.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.