

LNPT[™] LUBRICOMP[™] COMPOUND 5CL24

FP-VCL-4024

DESCRIPTION

LNP LUBRICOMP 5CL24 compound is based on Polyvinylidene Fluoride (PVDF) resin containing 10% PTFE and 20% carbon fiber. Added features of this grade include: Wear Resistant, Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyvinylidene Fluoride (PVDF)
Processing Techniques	Injection Molding

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Energy Management, Electronic Components
Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	117	MPa	ASTM D638
Tensile Strain, break	1.3	%	ASTM D638
Tensile Modulus, 50 mm/min	17070	MPa	ASTM D638
Flexural Stress	172	MPa	ASTM D790
Flexural Modulus	14820	MPa	ASTM D790
PHYSICAL ⁽¹⁾			
Density	1.78	g/cm ³	ASTM D792
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	215 – 230	°C	
Front - Zone 3 Temperature	225 – 245	°C	
Middle - Zone 2 Temperature	210 – 225	°C	
Rear - Zone 1 Temperature	190 – 210	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.