

LNPTM LUBRICOMPTM COMPOUND EFL36E

EFL-4036 EM

DESCRIPTION

LNP LUBRICOMP EFL36E compound is based on Polyetherimide (PEI) resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Easy Molding, Wear Resistant.

GENERAL INFORMATION

Features	Good Processability, Wear resistant, High stiffness/Strength, High temperature resistance
Fillers	Glass Fiber, PTFE
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical, Defense

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 5 mm/min	11400	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	140	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	8650	MPa	ASTM D790
Flexural Strength, 1.3 mm/min, 50 mm span	220	MPa	ASTM D790
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Stress, break, 5 mm/min	150	MPa	ISO 527
Tensile Modulus, 1 mm/min	11200	MPa	ISO 527
Flexural Modulus, 2 mm/min	8900	MPa	ISO 178
Flexural Strength, 2 mm/min	210	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	80	J/m	ASTM D256
Izod Impact, unnotched, 23°C	540	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	33	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	44	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	208	°C	ASTM D648
Vicat Softening Temp, Rate B/50	215	°C	ASTM D1525

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 60°C, flow	1.6E-05	1 / °C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.1E-05	1 / °C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	208	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	213	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/120	210	°C	ISO 306
Vicat Softening Temp, Rate B/50	215	°C	ISO 306
Relative Temp Index, Elec ⁽²⁾	105	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	105	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	105	°C	UL 746B
PHYSICAL ⁽¹⁾			
Dynamic COF	0.77	-	ASTM D3702 Modified: Manual
Static COF	0.63	-	ASTM D3702 Modified: Manual
Wear Factor Washer	57	10 ⁴ -10 in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1 – 0.2	%	ASTM D570
Water Absorption, (23°C/24hrs)	0.2 – 0.3	%	ASTM D570
Density	1.6	g/cm ³	ASTM D792
Melt Flow Rate, 350°C/2.16 kgf	8.2	g/10 min	ASTM D1238
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Water Absorption, (23°C/24hrs)	0.2 – 0.3	%	ISO 62-1
Melt Volume Rate, MVR at 350°C/2.16kg	5.3	cm ³ /10 min	ISO 1133
Density	1.6	g/cm ³	ISO 1183
Mold Shrinkage, flow ⁽³⁾	0.1 – 0.3	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.2 – 0.5	%	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-101343830	-	-
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 375	°C	
Rear - Zone 1 Temperature	355 – 365	°C	
Middle - Zone 2 Temperature	360 – 370	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Nozzle Temperature	365 – 375	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.