

LNPT[™] LUBRICOMP[™] COMPOUND FX04491H

PDX-F-04491

DESCRIPTION

LNP LUBRICOMP FX04491H compound is based on Polyethylene (PE) resin containing proprietary lubricant. Added features of this grade include: Wear Resistant, Healthcare

GENERAL INFORMATION

Features	Wear resistant, Healthcare/Formula lock, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyethylene, Unspecified (PE, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Hygiene and Healthcare
Packaging

SUB INDUSTRY

Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	24	MPa	ASTM D638
Tensile Strain, yield	7.4	%	ASTM D638
Flexural Stress	23	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	45	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	42	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	0.932	g/cm ³	ASTM D792
Wear Factor Washer	24	10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.13	-	ASTM D3702 Modified: Manual
Static COF	0.11	-	ASTM D3702 Modified: Manual
INJECTION MOLDING ⁽²⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	230	°C	
Front - Zone 3 Temperature	220 – 230	°C	
Middle - Zone 2 Temperature	210 – 220	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	40 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.