

LNPT[™] LUBRICOMP[™] COMPOUND IBP34

IBL-4534

DESCRIPTION

LNP LUBRICOMP IBP34 compound is based on Nylon 6/12 resin containing 20% glass bead, 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION

Features	Wear resistant, Dimensional stability
Fillers	Glass Bead, PTFE/Silicone
Polymer Types	Polyamide 612 (Nylon 612)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	45	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.6	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.9	%	ASTM D638
Tensile Modulus, 50 mm/min	2740	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	76	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2610	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.5	%	ISO 527
Tensile Strain, break, 5 mm/min	3.7	%	ISO 527
Tensile Modulus, 1 mm/min	2670	MPa	ISO 527
Flexural Stress	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2650	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	329	J/m	ASTM D4812
Izod Impact, notched, 23°C	28	J/m	ASTM D256
Multiaxial Impact	1	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	4	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	18	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	2	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	170	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	106	°C	ASTM D648
CTE, -30°C to 30°C, flow	8.8E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	8.7E-05	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	159	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	70	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.32	-	ASTM D792
Density	1.32	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.22	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽³⁾	2 – 4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	2 – 4	%	ASTM D955
Wear Factor Washer	13	10 ⁻⁴ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Wear Factor Ring	0	10 ⁻⁴ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.56	-	ASTM D3702 Modified: Manual
Static COF	0.59	-	ASTM D3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	0.26	%	ISO 62
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101345274	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.12 – 0.2	%	
Melt Temperature	270 – 275	°C	
Front - Zone 3 Temperature	270 – 280	°C	
Middle - Zone 2 Temperature	260 – 270	°C	
Rear - Zone 1 Temperature	255 – 265	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.