

LNPT[™] LUBRICOMP[™] COMPOUND LCL33

LCL-4033

REGION EUROPE

DESCRIPTION

LNP LUBRICOMP LCL33 compound is based on Polyetheretherketone (PEEK) resin containing 15% carbon fiber, 15% PTFE. Added features of this grade include: Wear Resistant, Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength, High temperature resistance
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	162	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.9	%	ISO 527
Tensile Modulus, 1 mm/min	14500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	230	MPa	ISO 178
Flexural Strain, break, 2 mm/min	2.7	%	ISO 178
Flexural Modulus, 2 mm/min	11700	MPa	ISO 178
Flexural Strain, break, 2 mm/min, 80°C	2.7	%	ISO 178
Flexural Strain, break, 2 mm/min, 120°C	2.7	%	ISO 178
Flexural Strain, break, 2 mm/min, 150°C	6	%	ISO 178
Flexural Strain, break, 2 mm/min, 200°C	6.3	%	ISO 178
Flexural Strain, break, 2 mm/min, 250°C	6.5	%	ISO 178
Flexural Stress, yield, 2 mm/min, 80°C	192	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 120°C	158	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 150°C	100	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 200°C	60	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 250°C	50	MPa	ISO 178
Flexural Modulus, 2 mm/min, 80°C	10300	MPa	ISO 178
Flexural Modulus, 2 mm/min, 120°C	10200	MPa	ISO 178
Flexural Modulus, 2 mm/min, 150°C	5700	MPa	ISO 178

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Flexural Modulus, 2 mm/min, 200°C	3000	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	34	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	9.5E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.3E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	>300	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Wear Factor Washer	17	10 ⁻⁴ in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.35	-	ASTM D3702 Modified: Manual
Static COF	0.28	-	ASTM D3702 Modified: Manual
Density	1.43	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 400°C/10.0 kg	6 – 8	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.E+03 – 1.E+05	Ω	ASTM D257
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	380 – 390	°C	
Front - Zone 3 Temperature	380 – 395	°C	
Middle - Zone 2 Temperature	365 – 375	°C	
Rear - Zone 1 Temperature	350 – 360	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.