

LNPT[™] LUBRICOMP[™] COMPOUND LCL33EXQ

LCL33EXQ

DESCRIPTION

LNP LUBRICOMP LCL33EXQ compound is based on Polyetheretherketone (PEEK) resin containing 15% carbon fiber, 15% PTFE. Added features of this grade include: Wear Resistant, Easy Molding, Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive, Good Processability, Wear resistant, Carbon fiber filled, High stiffness/Strength, High temperature resistance
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	185	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.8	%	ASTM D638
Tensile Modulus, 5 mm/min	16000	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	277	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	13400	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	181	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	13960	MPa	ISO 527
Flexural Stress	276	MPa	ISO 178
Flexural Modulus, 2 mm/min	13530	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	69	J/m	ASTM D256
Izod Impact, notched 80°10°4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	320	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Melt Flow Rate, 400°C/5.0 kgf	32	g/10 min	ASTM D1238
Specific Gravity	1.45	-	ASTM D792
Poisson's Ratio	0.43	-	ISO 527-1/2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Wear Factor Washer	14	10 ⁻⁴ -10 in ³ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.37	-	ASTM D3702 Modified: Manual
Static COF	0.35	-	ASTM D3702 Modified: Manual
INJECTION MOLDING ⁽²⁾			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.