

LNPT[™] LUBRICOMP[™] COMPOUND ML004S

ML-4040 HS

REGION ASIA

DESCRIPTION

LNP LUBRICOMP ML004S compound is based on Polypropylene (PP) resin containing 20% PTFE. Added features of this grade include: Wear Resistant, Heat Stabilized.

GENERAL INFORMATION

Features	Heat Stabilized, Wear resistant
Fillers	Unreinforced, PTFE
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	30	MPa	ASTM D638
Tensile Strain, break	6.2	%	ASTM D638
Tensile Modulus, 50 mm/min	1760	MPa	ASTM D638
Flexural Stress	41	MPa	ASTM D790
Flexural Modulus	1550	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	279	J/m	ASTM D4812
Izod Impact, notched, 23°C	26	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	62	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.03	g/cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽²⁾	1.4	%	ASTM D955

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.