

LNPT[™] LUBRICOMP[™] COMPOUND OFL38A

DESCRIPTION

LNP LUBRICOMP OFL38A compound is based on Polyphenylene Sulfide (PPS) branched resin containing 40% glass fiber and 15% PTFE. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION

Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyphenylene Sulfide, Branched (PPS, Branched)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	147	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	14700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	206	MPa	ISO 178
Flexural Modulus, 2 mm/min	12700	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	1.6E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	3.8E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	280	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	264	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	130	°C	UL 746B
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽³⁾	0.2	%	SABIC method
Density	1.8	g/cm ³	ISO 1183
ELECTRICAL ⁽¹⁾			
Comparative Tracking Index ⁽⁴⁾	175	V	IEC 60112

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-101658602	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.7	mm	UL 94
Glow Wire Ignitability Temperature, 2.0 mm	875	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Value shown here is based on internal measurement.

(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.