

# LNPT<sup>TM</sup> LUBRICOMP<sup>TM</sup> COMPOUND RX93237

## DESCRIPTION

LNP LUBRICOMP RX93237 compound is based on Nylon 6/6 resin containing PTFE, Silicone Oil and MoS<sub>2</sub>. Added features of this grade include: Internally Lubricated, Wear Resistant.

### GENERAL INFORMATION

|                       |                             |
|-----------------------|-----------------------------|
| Features              | Wear resistant              |
| Fillers               | Unreinforced, PTFE/Silicone |
| Polymer Types         | Polyamide 66 (Nylon 66)     |
| Processing Techniques | Injection Molding           |

### INDUSTRY

Automotive  
Consumer  
Electrical and Electronics  
Industrial

### SUB INDUSTRY

Automotive Under the Hood  
Sport/Leisure, Personal Accessory  
Mobile Phone - Computer - Tablets  
Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES                                         | TYPICAL VALUES | UNITS             | TEST METHODS |
|----------------------------------------------------|----------------|-------------------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>                   |                |                   |              |
| Tensile Stress, break, 5 mm/min                    | 59             | MPa               | ISO 527      |
| Tensile Strain, break, 5 mm/min                    | 4.9            | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min                          | 2700           | MPa               | ISO 527      |
| Flexural Stress, yield, 2 mm/min                   | 84             | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min                         | 2300           | MPa               | ISO 178      |
| <b>IMPACT <sup>(1)</sup></b>                       |                |                   |              |
| Izod Impact, unnotched 80*10*4 +23°C               | 45             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C                 | 5              | kJ/m <sup>2</sup> | ISO 180/1A   |
| <b>THERMAL <sup>(1)</sup></b>                      |                |                   |              |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm             | 219            | °C                | ISO 75/Bf    |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm              | 66             | °C                | ISO 75/Af    |
| <b>PHYSICAL <sup>(1)</sup></b>                     |                |                   |              |
| Mold Shrinkage on Tensile Bar, flow <sup>(2)</sup> | 1.8 – 2        | %                 | SABIC method |
| Density                                            | 1.24           | g/cm <sup>3</sup> | ISO 1183     |
| <b>INJECTION MOLDING <sup>(3)</sup></b>            |                |                   |              |
| Drying Temperature                                 | 80             | °C                |              |
| Drying Time                                        | 4              | Hrs               |              |
| Maximum Moisture Content                           | 0.15 – 0.25    | %                 |              |
| Melt Temperature                                   | 275 – 290      | °C                |              |
| Front - Zone 3 Temperature                         | 295 – 305      | °C                |              |
| Middle - Zone 2 Temperature                        | 280 – 295      | °C                |              |

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

| PROPERTIES                | TYPICAL VALUES | UNITS | TEST METHODS |
|---------------------------|----------------|-------|--------------|
| Rear - Zone 1 Temperature | 265 – 275      | °C    |              |
| Mold Temperature          | 80 – 95        | °C    |              |
| Back Pressure             | 0.2 – 0.3      | MPa   |              |
| Screw Speed               | 30 – 60        | rpm   |              |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

#### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.