

LNPT[™] LUBRICOMP[™] COMPOUND WP004

WL-4540

REGION EUROPE

DESCRIPTION

LNP LUBRICOMP WP004 compound is based on Polybutylene Terephthalate (PBT) resin containing 20% PTFE/silicone. Added features of this grade include: Wear Resistant.

GENERAL INFORMATION

Features	Wear resistant
Fillers	Unreinforced, PTFE/Silicone
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	37	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	11.3	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	61	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	1.32E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.23E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/120	218	°C	ISO 306
Vicat Softening Temp, Rate B/120	170	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	152	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	54	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.42	g/cm ³	ISO 1183



(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.