

LNPT[™] LUBRICOMP[™] COMPOUND WX12001J

DESCRIPTION

LNP LUBRICOMP WX12001J compound is based on Polybutylene Terephthalate (PBT) resin containing proprietary lubricant. Added features of this grade include: Internally Lubricated, Wear Resistant, Low Extractables, Healthcare, Food Contact compliant.

GENERAL INFORMATION

Features	Wear resistant, Food contact, Healthcare/Formula lock
Fillers	Proprietary Filler, Unreinforced
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Hygiene and Healthcare
Packaging

SUB INDUSTRY

Water Management
Home Appliances
Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial Packaging, Food & Beverage

TYPICAL PROPERTY VALUES

Revision 20230713

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	54	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	10	%	ISO 527
Tensile Strain, break, 50 mm/min	13	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Strength, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80°10°4 +23°C	47	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	3	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	4	kJ/m ²	ISO 179/1eA
PHYSICAL ⁽¹⁾			
Wear Factor Washer	111	10 ⁻⁴ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Instr.
Dynamic COF	0.31	-	ASTM D3702 Modified: Instr.
Static COF	0.48	-	ASTM D3702 Modified: Instr.
Density	1.34	g/cm ³	ISO 1183
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.06	%	ISO 62-4
Melt Volume Rate, MVR at 250°C/2.16 kg	25	cm ³ /10 min	ISO 1133
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120	°C	
Drying Time	4	Hrs	

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.05	%	
Melt Temperature	240 – 265	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	220 – 230	°C	
Mold Temperature	80 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.