

LNPTM STAT-KONTM COMPOUND DX03550

PDX-D-03550

DESCRIPTION

LNP STAT-KON DX03550 compound is based on Polycarbonate (PC) resin containing conductive carbon powder. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive
Fillers	Carbon Powder
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding, Extrusion

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Electronic Components
Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	58	MPa	ASTM D638
Tensile Strain, break	20	%	ASTM D638
Tensile Modulus, 50 mm/min	2750	MPa	ASTM D638
Flexural Stress	96	MPa	ASTM D790
Flexural Modulus	2750	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	106	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	129	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.25	g/cm ³	ASTM D792
ELECTRICAL ⁽¹⁾			
Volume Resistivity ⁽²⁾	1.E+04 – 1.E+07	Ω.cm	ASTM D257
Surface Resistivity ⁽²⁾	1.E+04 – 1.E+07	Ω	ASTM D257
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	
FILM EXTRUSION ⁽¹⁾			
Drying Time	4	Hrs	
Drying Temperature	120 – 120	°C	
Barrell Temperature - Rear	250 – 280	°C	
Barrell Temperature - Middle	260 – 300	°C	
Barrell Temperature - Front	260 – 300	°C	
Roll Temperature	80 – 100	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurement meets requirements as specified in ASTM D4496.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.