

LNPTM STAT-KONTM COMPOUND KE005

REGION EUROPE

DESCRIPTION

LNP STAT-KON KE005 compound is based on POM (Acetal) copolymer resin containing 25% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION

Applications	Document Handling, Monitoring and Imaging
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Acetal (POM) Copolymer
Processing Techniques	Injection Molding
Regional Availability	Europe, Asia, Americas

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Electrical Components and Infrastructure
Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	100	MPa	ASTM D638
Tensile Strain, break	0.9	%	ASTM D638
Tensile Modulus, 5 mm/min	15500	MPa	ASTM D638
Flexural Stress	130	MPa	ASTM D790
Flexural Modulus	15000	MPa	ASTM D790
Tensile Stress, break	90	MPa	ISO 527
Tensile Strain, break	1.0	%	ISO 527
Tensile Modulus, 1 mm/min	13300	MPa	ISO 527
Flexural Stress	125	MPa	ISO 178
Flexural Modulus	15000	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	230	J/m	ASTM D4812
Izod Impact, notched, 23°C	170	J/m	ASTM D256
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	4.4	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eU
Izod Impact, unnotched 80*10*4 +23°C	5.8	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	163	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	161	°C	ASTM D648

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	1.0E-05	1/°C	ASTM E83 1
CTE, -40°C to 40°C, xflow	1.0E-04	1/°C	ASTM E83 1
Vicat Softening Temp, Rate A/120	164	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	154	°C	ASTM D1525
CTE, -40°C to 40°C, flow	1.0E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.0E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	162	°C	ISO 75/Af
Vicat Softening Temp, Rate A/120	164	°C	ISO 306
Vicat Softening Temp, Rate B/120	154	°C	ISO 306
PHYSICAL ⁽¹⁾			
Density	1.46	g/cm ³	ASTM D792
Water Absorption, (23°C/24hrs)	0.3 – 0.5	%	ASTM D570
Mold Shrinkage, xflow	0.9 – 1.1	%	SABIC method
Mold Shrinkage, flow	0.3 – 0.5	%	SABIC method
Melt Volume Rate, MVR at 190°C/5.0 kg	6 – 10	cm ³ /10 min	ISO 1133
Density	1.46	g/cm ³	ISO 1183
ELECTRICAL ⁽¹⁾			
Surface Resistivity, ROA	1.0E+01 – 1.0E+03	Ω	IEC 60093
Surface Resistivity ⁽²⁾	1.0E+01 – 1.0E+03	Ω	ASTM D257
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	200 – 215	°C	
Front - Zone 3 Temperature	210 – 220	°C	
Middle - Zone 2 Temperature	195 – 205	°C	
Rear - Zone 1 Temperature	175 – 190	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurement meets requirements as specified in ASTM D4496.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.