

LNPTM STAT-KONTM COMPOUND OE002

OC-1002

REGION AMERICAS

DESCRIPTION

LNP STAT-KON OE002 compound is based on Polyphenylene Sulfide (PPS) linear resin containing 10% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyphenylene Sulfide, Linear (PPS, Linear)
Processing Techniques	Injection Molding

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Electronic Components
Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	95	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	95	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	1.7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D638
Tensile Modulus, 5 mm/min	7390	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	141	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	142	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	6440	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	96	MPa	ISO 527
Tensile Stress, break, 5 mm/min	96	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	1.7	%	ISO 527
Tensile Strain, break, 5 mm/min	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	7500	MPa	ISO 527
Flexural Stress	148	MPa	ISO 178
Flexural Modulus, 2 mm/min	6520	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	370	J/m	ASTM D4812
Izod Impact, notched, 23°C	43	J/m	ASTM D256
Multiaxial Impact	1	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	7	J	ASTM D3763
Izod Impact, unnotched 80°10°4 +23°C	18	kJ/m ²	ISO 180/1U

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 +23°C	2	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	263	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	189	°C	ASTM D648
CTE, -30°C to 30°C, flow	2.7E-05	1/°C	ASTM D696
CTE, -30°C to 30°C, xflow	5.2E-05	1/°C	ASTM D696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	259	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	122	°C	ISO 75 /Af
PHYSICAL ⁽¹⁾			
Specific Gravity	1.38	-	ASTM D792
Density	1.377	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/ 24 hrs)	0.01	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.5 – 0.8	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	0.6 – 0.9	%	ASTM D955
Moisture Absorption (23°C / 50% RH)	0.02	%	ISO 62
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽³⁾	1.E+03 – 1.E+06	Ω	ASTM D257
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.